



**AUTHORIZED DISTRIBUTOR**  
**1-800-448-0406**

*Silicones Simplified*  
 www.xiameter.com



## XIAMETER® brand High Consistency Rubber (HCR) Bases – Americas Selection Guide

Product Series	XIAMETER® Product Name	Peroxide Catalyst Type	Cure Profile	Hardness, Shore A	Tensile, MPa	Elongation, %	Tear, kN/m	Plasticity, mm / 100	Compression Set, %	Specific Gravity	Modulus 100%, MPa
<b>HCR Bases</b>											
<b>General Purpose</b>											
XIAMETER® RBB-2000/ RBB-2001 Series	XIAMETER® RBB-2000-35 Base	2,4-dichlorobenzoyl peroxide - 50% active (1.1 pph)	Press Cure: 5'/116°C Post Cure: 4 h/200°C	35	7.8	705	13	150	24	1.1	0.6
	XIAMETER® RBB-2001-65 Base	2,4-dichlorobenzoyl peroxide - 50% active (1.5 pph)	Press Cure: 5'/116°C Post Cure: 4 h/200°C	71	10.1	320	18	300	18	1.2	2.9
XIAMETER® RBB-2002 Series	XIAMETER® RBB-2002-30 Base	2,5-bis(tert-butylperoxy) -2,5-dimethylhexane - 45% active (1 pph)	Post Cure: 10'/171°C Post Cure 1h/250°C	35	6	585	10	150	NA	1.09	0.6
	XIAMETER® RBB-2002-45 Base	2,4-dichlorobenzoyl peroxide - 50% active (1.2 pph)	Press Cure: 5'/116°C Post Cure: 4 h/200°C	48	8.1	445	11	220	NA	1.13	1.1
	XIAMETER® RBB-2002-50 Base	2,4-dichlorobenzoyl peroxide - 50% active (1.2 pph)	Press Cure: 5'/116°C Post Cure: 4 h/200°C	52	8.8	430	13	260	NA	1.15	1.2
	XIAMETER® RBB-2002-70 Base	2,5-bis(tert-butylperoxy) -2,5-dimethylhexane - 45% active (1 pph)	Post Cure: 10'/171°C Post Cure 1h/250°C	67	7.1	490	27	350	NA	1.23	1.6
XIAMETER® RBB-2300-30 Base	XIAMETER® RBB-2300-30 Base	2,5-bis(tert-butylperoxy) -2,5-dimethylhexane - 45% active (1 pph)	Press Cure: 10'/171°C	35	6.6	730	11	190	13	1.1	0.4
<b>No Post Cure</b>											
XIAMETER® RBB-2030 Series	XIAMETER® RBB-2030-40 Base	2,5-bis(tert-butylperoxy) -2,5-dimethylhexane - 45% active (1 pph)	Press Cure: 10'/171°C	40	7.2	575	11	150	14	1.11	0.8
	XIAMETER® RBB-2030-80 Base	2,5-bis(tert-butylperoxy) -2,5-dimethylhexane - 45% active (1 pph)	Press Cure: 10'/171°C	85	8	90	15	270	13	1.43	NA
<b>Tear Resistant</b>											
XIAMETER® RBB-2220 Series	XIAMETER® RBB-2220-55 Base	2,5-bis(tert-butylperoxy) -2,5-dimethylhexane - 45% active (1 pph)	Press Cure: 10'/171°C	55	10.6	785	51	210	34	1.15	2.1
	XIAMETER® RBB-2220-70 Base	2,5-bis(tert-butylperoxy) -2,5-dimethylhexane - 45% active (1 pph)	Press Cure: 10'/171°C	70	8.7	540	51	250	27	1.2	4
<b>High Strength</b>											
XIAMETER® RBB-2210 Series	XIAMETER® RBB-2210-30 Base	2,4-dichlorobenzoyl peroxide - 50% active (0.8 pph)	Press Cure: 5'/116°C Post Cure: 4 h/200°C	30	9.1	1120	35	170	32	1.14	0.6

Product Series	XIAMETER® Product Name	Peroxide Catalyst Type	Cure Profile	Hardness, Shore A	Tensile, MPa	Elongation, %	Tear, kN/m	Plasticity, mm / 100	Compression Set, %	Specific Gravity	Modulus 100%, MPa
	XIAMETER® RBB-2210-50 Base	2,4-dichlorobenzoyl peroxide - 50% active (1.3 pph)	Press Cure: 5'/116°C Post Cure: 4 h/200°C	50	9	690	34	220	27	1.19	1.2
	XIAMETER® RBB-2210-70 Base	2,5-bis(tert-butylperoxy) -2,5- dimethylhexane - 45% active (1.2 pph)	Post Cure: 10'/171°C Post Cure 4 h/200°C	70	9.9	515	36	290	30	1.22	2.4
<b>Low Temperature</b>											
XIAMETER® RBB-2060 Series	XIAMETER® RBB-2060-40 Base	2,4-dichlorobenzoyl peroxide - 50% active (0.6 pph)	Press Cure: 5'/116°C Post Cure: 4 h/200°C	40	7.2	625	11	160	18	1.13	0.06
	XIAMETER® RBB-2060-50 Base	2,5-bis(tert-butylperoxy) -2,5- dimethylhexane - 45% active (1.0 pph)	Post Cure: 10'/171°C Post Cure 4 h/200°C	50	8.9	630	32	120	27	1.21	1.2
<b>Wire and Cable</b>											
XIAMETER® RBB-2340 Series	XIAMETER® RBB-2340-50 Base	2,4-dichlorobenzoyl peroxide - 50% active (1.3 pph)	Press Cure: 5'/116°C	50	10.1	465	18	330	NA	1.17	1.3
	XIAMETER® RBB-2340-60 Base	2,5-bis(tert-butylperoxy) -2,5- dimethylhexane - 45% active (1.0 pph)	Press Cure: 10'/171°C	60	9.9	540	23	NA	NA	1.17	NA
	XIAMETER® RBB-2340-70 Base	2,4-dichlorobenzoyl peroxide - 50% active (1.5 pph)	Press Cure: 5'/121°C	70	9.9	375	19	350	NA	1.2	2.4
<b>Low Compression Set</b>											
XIAMETER® RBB-2380	XIAMETER® RBB-2380-40 Base	2,5-bis(tert-butylperoxy) -2,5- dimethylhexane - 45% active (1.0 pph)	Press Cure: 10'/171°C	45	4.6	345	7	180	8	1.09	1.1

**Typical Properties** – Specification Writers: These values are not intended for use in preparing specifications. Please contact your local XIAMETER® sales representative prior to writing specifications on these products.

## Contact Us

### LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

*Dow Corning* and XIAMETER are registered trademarks of Dow Corning Corporation.

©2011 Dow Corning Corporation. All rights reserved.

Printed in USA

AGP11096

Form No. 95-746-01



**AUTHORIZED DISTRIBUTOR  
1-800-448-0406**

Silicones Simplified  
**XIAMETER**  
from DOW CORNING